


Cuerpo tensor M-6 AISI 316

MATERIA PRIMA AISI 316

Ø10mm C 0,04% - Si 0,38% - Mn 1,29% - P 0,04% - S 0,01% - Cr 16,84% - Ni 10,35% - Mo 2,14% - N 0,40%

Ø13.5mm C 0,02% - Si 0,32% - Mn 1,63% - P 0,03% - S 0,03% - Cr 16,80% - Ni 10,00% - Mo 2,02% - N 0,03%



Code Number	Carga de Rotura (B.L.)	L	L1	D	D1	D2	G
716011206	1.000 kg	65	12,5	10	7,8	3	M-6

Fabricación según norma UNE-EN 13241-1-2004

