


Cuerpo tensor M-10 AISI 316

MATERIA PRIMA AISI 316

Ø10mm C 0,04% - Si 0,38% - Mn 1,29% - P 0,04% - S 0,01% - Cr 16,84% - Ni 10,35% - Mo 2,14% - N 0,40%

Ø13.5mm C 0,02% - Si 0,32% - Mn 1,63% - P 0,03% - S 0,03% - Cr 16,80% - Ni 10,00% - Mo 2,02% - N 0,03%



Code Number	Carga de Rotura (B.L.)	L	L1	D	D1	D2	G
716011210	2.500 kg	85	15	17.2	12	5	M-10

Fabricación según norma UNE-EN 13241-1-2004

