


Tensor "C-4mm" rosca externa izquierda M-6 AISI 316

MATERIA PRIMA AISI 316

Ø6,3mm C 0,07% - Si 0,43% - Mn 1,23% - P 0,03% - S 0,01% - Cr 16,21% - Ni 10,49% - Mo 2,00% - N 0,03%

Ø7,5mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni 10,25% - Mo 2,15% - N 0,50%

Ø9mm C 0,04% - Si 0,38% - Mn 1,29% - P 0,04% - S 0,01% - Cr 16,84% - Ni 10,35% - Mo 2,14% - N 0,40%



Code Number	Carga de Rotura (B.L)	Ø	L	L1	L2	D	D1	G
716180604	1.000 kg	4	65	25	30	6,3	5,3	M-6

Fabricación según norma UNE-EN 13241-1-2004

