


Tensor "C-6mm" rosca interna derecha M-8 AISI 316

MATERIA PRIMA AISI 316

Ø8mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni10,25% - Mo2,15% - N0,50%

Ø8mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni10,25% - Mo2,15% - N0,50%

Ø11mm C 0,02% - Si 0,32% - Mn 1,63% - P 0,03% - S 0,03% - Cr 16,80% - Ni10,00% - Mo2,02% - N0,03%



Code Number	Carga de Rotura (B.L)	Ø	L1	L2	L3	L4	D1	D2	D3	G
716040606	2.000 kg	6	85	40	25	40	11	9	6,5	M-8

Fabricación según norma UNE-EN 13241-1-2004

