


Tensor "C-5mm" rosca interna izquierda M-6 AISI 316

MATERIA PRIMA AISI 316

Ø8mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni10,25% - Mo2,15% - N0,50%

Ø8mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni10,25% - Mo2,15% - N0,50%

Ø11mm C 0,02% - Si 0,32% - Mn 1,63% - P 0,03% - S 0,03% - Cr 16,80% - Ni10,00% - Mo2,02% - N0,03%



Code Number	Carga de Rotura (B.L)	Ø	L1	L2	L3	L4	D1	D2	D3	G
716140605	1.500 kg	5	70	30	20	35	8	7,5	5,3	M-6

Fabricación según norma UNE-EN 13241-1-2004

