

Tensor anclaje derecha M-6 AISI 316

MATERIA PRIMA AISI 316

Ø6mm C 0,07% - Si 0,43% - Mn 1,23% - P 0,03% - S 0,01% - Cr 16,21% - Ni 10,49% - Mo 2,00% - N 0,03%

Ø8mm C 0,06% - Si 0,41% - Mn 1,52% - P 0,04% - S 0,02% - Cr 16,47% - Ni 10,25% - Mo 2,15% - N 0,50%



Code Number	Carga de Rotura (B.L)	L1	L2	L3	G	D
716990600	1.000 kg	80	35	35	6	M-6

Fabricación según norma UNE-EN 13241-1-2004

