


HUTMUTTER M-6 AISI 316

ROHSTOFF AISI 316

Ø10mm C 0,04% - Si 0,38% - Mn 1,29% - P 0,04% - S 0,01% - Cr 16,84% - Ni 10,35% - Mo 2,14% - N 0,40%

Ø13mm C 0,02% - Si 0,32% - Mn 1,63% - P 0,03% - S 0,03% - Cr 16,80% - Ni 10,00% - Mo 2,02% - N 0,03%



Referenz	Last Brechen (B.L)	A	G
95007	1.000 kg	10	M-6

Fabricación según norma UNE-EN 13241-1-2004

